

## KOPELEN JM-370

## PP BLOCK COPOLYMER

### General Information

#### Description

JM-370 is high impact block copolymer which has more ethylene contents than normal block copolymer.

This grade is designed to be processed in conventional Injection molding equipment.

JM-370 shows better impact resistance than normal block copolymer and has good physical property balance.

#### Applications

- ◆ Industrial supplies
- ◆ Automotive compound base resin

### Physical Properties<sup>1</sup>

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	35	g/10min		
Density	ASTM D792	0.90	g/cm <sup>3</sup>		
<b>Mechanical</b>					
Tensile Stress (Yield)	ASTM D638	260	kgf/cm <sup>2</sup>	25	MPa
Tensile Strain (Break)	ASTM D638	>50	%	>100	%
Flexural Modulus	ASTM D790	13,000	kgf/cm <sup>2</sup>	1,270	MPa
<b>Impact</b>					
Notched Izod Impact Strength (23 °C)	ASTM D256	7.5	kgf-cm/cm	74	J/m
Notched Izod Impact Strength (-10 °C)	ASTM D256	3.5	kgf-cm/cm	34	J/m
<b>Thermal</b>					
Heat Deflection Temperature (4.6kgf/cm <sup>2</sup> )	ASTM D648	105	°C		
<b>Additional Properties</b>					
Flammability	UL94	HB			

### NOTE

ISO 9001, 14001, /ITS 16949

<sup>1</sup> Physical Properties : these are not to be construed as specifications

## KOPELEN JM-370

## PP BLOCK COPOLYMER

### General Information

#### Description

JM-370 is high impact block copolymer which has more ethylene contents than normal block copolymer.

This grade is designed to be processed in conventional Injection molding equipment.

JM-370 shows better impact resistance than normal block copolymer and has good physical property balance.

#### Applications

- ◆ Industrial supplies
- ◆ Automotive compound base resin

### Physical Properties<sup>1</sup>

Physical	Test Method	Nominal Values			
Melt Flow Index	ISO 1133	35	g/10min		
Density	ISO 1183	0.90	g/cm <sup>3</sup>		
<b>Mechanical</b>					
Tensile Stress (Yield)	ISO 527-1	250	kgf/cm <sup>2</sup>	25	MPa
Tensile Strain (Break)	ISO 527-1	<100	%	<100	%
Flexural Modulus	ISO 178	11,000	kgf/cm <sup>2</sup>	1,080	MPa
<b>Impact</b>					
Notched Izod Impact Strength (23 °C)	ISO 180	7	kgf-cm/cm	69	J/m
Notched Izod Impact Strength (-10 °C)	ISO 180	3	kgf-cm/cm	29	J/m
<b>Thermal</b>					
Heat Deflection Temperature (4.6kgf/cm <sup>2</sup> )	ISO 75-1	85	°C		
<b>Additional Properties</b>					
Flammability	UL94	HB			

### NOTE

ISO 9001, 14001, /TS 16949

<sup>1</sup> Physical Properties : these are not to be construed as specifications