

KOPELEN JM-365

PP BLOCK COPOLYMER

General Information

Description

JM-365 is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in conventional Injection molding equipment. JM-365 shows better impact resistance than normal block copolymer and has good physical property balance.

Applications

- ◆ Industrial supplies
- ◆ Automotive compound base resin

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	26	g/10min		
Density	ASTM D792	0.9	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ASTM D638	260	kgf/cm ²	25	MPa
Tensile Strain (Break)	ASTM D638	>50	%	>50	%
Flexural Modulus	ASTM D790	13,000	kgf/cm ²	1,270	MPa
Impact					
Notched Izod Impact Strength (23℃)	ASTM D256	7.0	kgf-cm/cm	69	J/m
Notched Izod Impact Strength (-10℃)	ASTM D256	4.0	kgf-cm/cm	39	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm ²)	ASTM D648	105	℃		
Additional Properties					
Flammability	UL94	-			

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

KOPELEN JM-365

PP BLOCK COPOLYMER

General Information

Description

JM-365 is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in conventional Injection molding equipment. JM-365 shows better impact resistance than normal block copolymer and has good physical property balance.

Applications

- ◆ Industrial supplies
- ◆ Automotive compound base resin

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ISO 1133	26	g/10min		
Density	ISO 1183	0.9	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ISO 527-1	250	kgf/cm ²	25	MPa
Tensile Strain (Break)	ISO 527-1	<100	%	<100	%
Flexural Modulus	ISO 178	11,000	kgf/cm ²	1,080	MPa
Impact					
Notched Izod Impact Strength (23℃)	ISO 180	6.5	kgf-cm/cm	64	J/m
Notched Izod Impact Strength (-10℃)	ISO 180	3.5	kgf-cm/cm	34	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm ²)	ISO 75-1	85	℃		
Additional Properties					
Flammability	UL94	-			

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications