Polypropylene Random Copolymer for Injection Molding

P753J (Provisional datasheet)

Product Description

EL-Pro P753J is a random copolymer polypropylene resin which has ultra high clarity, high flowability and contains anti-static agent suitable for injection molding process.

Typical Application

Product Characteristics

- Household product
- Clear food and large size containers

- Super high clarity and good processibility
- Good impact strenght with stiffness balance
- Food contact applicable (complies with U.S. FDA 21 CFR 177.1520)

Physical Properties

Property	Test Method	Value	Unit
Haze (at 1 mm)	ASTM D1003	5	%
Melt Flow Rate	ASTM D 1238 @ 230°C, 2.16 kg	20	g/10 min
Density	ASTM D 1505	0.910	g/cm ³
Tensile Strength at Yield	ASTM D 638 @ Crosshead speed 50 mm/min	320	kg/cm ²
Elongation at Break	ASTM D 638 @ Crosshead speed 50 mm/min	700	%
Flexural Modulus	ASTM D 790	12500	kg/cm ²
Notched Izod Impact	ASTM D 256 @ 23°C	6	kg.cm/cm
Notched Izod Impact	ASTM D 256 @ 0°C	4	kg.cm/cm
Melting Point	ASTM D 2117	150	°C
Vicat Softening Point	ASTM D 1525	130	°C
Heat Deflection Temperature (HDT)	ASTM D 648 @ 4.6 kg/cm ²	100	°C

Note: Conversion factor for changing unit from kg/cm² to MPa is divided by 10.20

Processing Techniques

The actual processing conditions depend on each machine type, product size, mold design and environment.

Recommended processing conditions:

Melt temperature: 190-260°C Mold temperature: 20-40°C Injection speed: Fast Screw speed 40-70 rpm Pressure: Injection 40-80%, Packing and Holding 30-60%, Back 10% of Max. Pressure

Product Available Form Product Handling

Pellet
25 kg loose bag

Product Technical Assistance

For technical assistance or futher information on this product or any other EL-Pro products, please contact EL-Pro representatives.

The information presented in this data sheet is offered in good faith. SCG Plastics Co., Ltd. accepts no responsibility for the accuracy or interpretation of the information presented. The users have to establish for yourself the most suitable formulation, production method and control tests, to ensure the uniformity and quality of your product in compliance with all related laws.

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

Recycling

- The product is suitable for reclycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

Related Documents

- The lastest version of this document will be available at our website, www.chemicals.scg.co.th, or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Data Sheet
 - Statement on compliance to food contact regulations

Disclaimer

- The product can be used only for the application as specified hereabove.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.
- We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.
- No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.



are registered trademarks of SCG Chemicals, Thailand.

SCG Plastics Company Limited / SCG Performance Chemicals Company Limited

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand.

Tel. +66 2586 4874 Fax +66 2586 5522

www.chemicals.scg.co.th