

REPSOL ISPLEN PB130G1F

REPSOL ISPLEN PB130G1F is a phthalate free heterophasic copolymer designed for extrusion applications. It includes thermal stabilisers to protect the polymer during processing and handling.

It offers optical processability and high impact strength, even at low temperatures.

Applications

Due to its optimal balance of properties the grade REPSOL ISPLEN PB130G1F is especially suited for applications that require excellent mechanical properties, such as:

- Films with excellent tear resistance and impact strength for special applications
- Sheets and profiles
- Pipes .
- Blow-moulding .

Recommended melt temperatures range between 190 and 250°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt flow rate (230°C/ 2,16 kg)	1.3	g/10 min	ISO 1133
Density at 23°C	905	kg/m ³	ISO 1183
MECHANICAL			
Flexural Modulus	1200	MPa	ISO 178
Tensile strength at yield	27	MPa	ISO 527-2
Charpy impact strength (23°C, notched)	35	kJ/m ²	ISO 179
Charpy impact strength (-20°C, notched)	5	kJ/m ²	ISO 179
THERMAL			
Vicat softening temperature A120 (10 N)	150	°C	ISO 306
HDT 0.45MPa	75	°C	ISO 75
OTHERS			
Shore Hardness	60	-	ISO 868

Storage

REPSOL ISPLEN PB130G1F should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

[1/2]

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development: Headquarters Repsol Technology Lab Ctra. de Extremadura A5, Km 18 28931 Móstoles Tel. +34 91 753 85 00 atd_poliolefinas@repsol.com

Méndez Álvaro, 44 28045 Mədrid España www.repsol.com

Customer Care sacrg@repsol.com



Technical Data Sheet Chemicals



Disclaimer

This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet .
- Statement on compliance with food contact regulations

Recommended consumption period: 12 months from the raw material reception

July 2021

[2/2]

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registeres desings cannot be assumed.

Technical Service and Development: Headquarters Repsol Technology Lab Ctra. de Extremadura A5, Km 18 28931 Móstoles Tel. +34 91 753 85 00 atd_poliolefinas@repsol.com

Méndez Álvaro, 44 28045 Madrid España www.repsol.com

Customer Care sacro@repsol.com

