

## DESCRIPTION

Styrolution PS 495N is an impact resistant polystyrene with a good balance of toughness, high flow, heat resistance and high gloss.

## FEATURES

- High flow
- Good balance of toughness and heat resistance

## APPLICATIONS

- Injection molding
- TV & office equipment components
- Air conditioners
- Water tanks for toilet flushing

Property, Test Condition	Standard	Unit	Values
<b>Rheological Properties</b>			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm <sup>3</sup> /10 min	9.5
<b>Mechanical Properties</b>			
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m <sup>2</sup>	17
Tensile Stress at Yield, 23 °C	ISO 527	MPa	26
Tensile Strain at Yield, 23 °C	ISO 527	%	1.5
Tensile Modulus	ISO 527	MPa	2000
Elongation at Break (MD)	ISO 527	%	40
Flexural Strength, 23 °C	ISO 178	MPa	40
Flexural Modulus, 23 °C	ISO 178	MPa	2100
Hardness, Ball Indentation	ISO 2039-1	MPa	74
<b>Thermal Properties</b>			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	89
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	85
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	89
Coefficient of Linear Thermal Expansion	ISO 11359	10 <sup>-6</sup> /°C	80
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
<b>Electrical Properties</b>			

# Styrolution PS 495N

High Impact Polystyrene (HIPS)

## TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Dielectric Constant (100 Hz)	IEC 62631-2-1	-	2.5
Dissipation Factor (100 Hz)	IEC 62631-2-1	10 <sup>-4</sup>	4
Dissipation Factor (1 MHz)	IEC 62631-2-1	10 <sup>-4</sup>	4
Volume Resistivity	IEC 62631-3-1	Ohm*m	>10 <sup>16</sup>
Surface Resistivity	IEC 62631-3-1	Ohm	>10 <sup>13</sup>
<b>Optical Properties</b>			
<b>Other Properties</b>			
Density	ISO 1183	kg/m <sup>3</sup>	1040
<b>Processing</b>			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	180 - 260

Typical values for uncolored products

## SUPPLY FORM

Styrolution PS 495N is supplied as cylindrical shaped granules. It has to be kept in its original containers in a cool, dry place. Avoid direct exposure to sunlight. Styrolution PS can be stored in silos.

## PROCESSING

Styrolution PS 495N can be injection molded under different conditions depending on machinery available and articles molded. Mass temperature can be as high as 260°C. Styrolution PS 495N is suitable for gas assisted injection molding. To achieve articles with very high gloss, well-polished surfaces are recommended.

## PRODUCT SAFETY

During processing of Styrolution PS small quantities of styrene monomer may be released into the atmosphere. At styrene vapor concentrations below 20ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well ventilated workplaces - that is were five to eight air changes per hour are made.

---

**DISCLAIMER**

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.

---